
Material	Density/(kg m ⁻³)	Bulk/GPa	Shear/GPa
SSiC	3100	200	180
Stone	2500	40	18
Foundation	2400	60	40
